

# VITRIFIED CENTERLESS GRINDING WHEELS

# Special two layers harder face design


To satisfied the right-angle retention requirements of work.

VITRIFIED CENTERLESS GRINDING WHEELS Anchor Centerless Wheels are available in a range of specifications for high metal removal rates and optimum wheel life.

# CENTERLESS GRINDING

## CENTERLESS GRINDING METHOD

Centerless grinding differs from cylindrical grinding operations in that no spindle or fixture is used to locate and secure the work piece; the work piece is secured between a centerless grinding wheel and a regulating wheel.



nchor

## REGULATING WHEELS and MACHINE TYPE

Regulating wheels are always made by resin bond, the main function include:

- A. Control the feed rate and speed of work piece.
- B. Secure the work piece.
- C. Control the diameter of work piece.

#### Wheel and Regulating wheel size comparative table / Unit : mm


Grinding Wheel Size		Regulating Wheel Size		
Diameter	Thickness	Diameter	Thickness	
305	100 150 205	205	100 150 205	
355	150 205	205	150 205	
405	150 205	255	150 205	
455	150 205 255 305	255	150 205 255 305	
510	150 205 255 305	305	150 205 255 305	
610	205 255 305	305	205 255 305	

## SPICIFICATION

#### ■ Standard size of centerless grinding ( unit : mm )

TYPE	SHAPE	SIZE						
		D	Т	н	Р	E	F	G
12"Centerless	7A	305	150	120	175	100	25	25
12"Regulating	7A	205	150	90	130	100	25	25
18" Centerless	7A	455	205	228.6	295	155	25	25
18" Regulating	7A	255	205	111.2	170	110	75	20
20" Centerless	7A	510	205	254	320	155	25	25
20" Regulating	7A	305	205	127	190	110	75	20
20" Centerless	7A	510	205	304.8	360	155	25	25
20" Regulating	7A	305	205	127	200	103	63.5	38.5

■ The standard shape and face 7A of centerless wheel.



#### ■ Regular specifications of centerless and regulating wheels

Material	Application	Specification	
S09CK、S45C、SK1~7 SMn、SCr、SCM、SNCM	Without special treatment softer hardness	<b>38A 60-80 L</b> WA 60-80 L A 60-80 L	
SKS、SKD、SKT SUH 1、3、4 SKH	Heat treated with harder hardness or higher retention requirements	50A 80-100 L	
SUJ2、SUJ3 Iron	Two layers of harder face design to satisfied the right-angle retention requirements of work	38A 80 LM/NO 50A 80-100 LM/NO 64A 80-100 M/O	
SUS 300 400 FC FCMW、FCMB、FCMP Chrome plated Copper, aluminum, plastic, rubber and so on	Non-ferrous material	GC 60-80 K GC 60-80 L	

■ Special two layers of harder face design for several specifications of 305mm and 455mm standard size.

■ For any further inquiry, please contact us via the company information below.

COMPANY INFORMATION	CARBO TZUJAN INDUSTRIAL CO., LTD		
<ul> <li>For details, please contact the following agency.</li> </ul>	INFORMATION: TEL : +886-2-2679-3461 FAX : +886-2-2679-4561 Head Office: 220 No. 1 Ev. An St. Ving Ke		

Head Office: 239 No.1 Fu An St. Ying Ko District, New Taipei City, Taiwan.

CONTACT US:

- Online service : <u>www.carbo.com.tw</u>
- E-mail : webmaster@carbo.com.tw



While using grinding wheels, it is essential that you observe correct procedures to protect yourself.